


## 1. Application / Construction

Identification	GYFXT6P-6 G.652D		
Application	Duct Installation Cable		
Cross Section (not to scale)	 <p>6 fibers</p>		
Configuration	<ul style="list-style-type: none"> <li>- Micro module with up to 6 optical fibres and jelly inside</li> <li>- Easy to strip the micro module</li> <li>- 2 Parallel strength members (FRP) in the cable sheath</li> <li>- Cable strand: dry, with water blocking yarns and water blocking tape</li> <li>- Glass yarns as additional strength member</li> <li>- Outer sheath: Black PE, UV proof</li> </ul>		
Temperature Range	Storage and transport -30 to +70°C	Installation -5 to +50°C	Operation -20 to +60°C
Standards	IEC 60793-1, IEC 60793-2, IEC 60794-3-10, ITU-T G.652		
ZTT Specification	21-116461-12-B		
Customer Reference	3424011121		

## 2. Dimensions

Number of fibers		6
Fiber No. per module		6
No. of micro module		1
Outer sheath thickness	mm	Min. 1.3
Outer diameter ( $\pm 5\%$ )	mm	6.6
Weight/km	kg	30

Note: sizes and values without tolerances are nominal values

## 3. Mechanical Properties

Max. tensile load (N)	600
Crush resistance (N/10cm)	1000
Bending radius (installation)	20x cable Ø
Bending radius (operation)	10x cable Ø

See Point 7: Test Methods

## 4. Marking

Fiber Colors	1	2	3	4	5	6		
	red	green	blue	yellow	white	grey		
Tube Color	<table border="1" style="display: inline-table; vertical-align: middle;"> <tr> <td>1</td> </tr> <tr> <td>red</td> </tr> </table>						1	red
1								
red								

Outer Sheath: black, ink jet or hot print, marking in 1 meter intervals as follows (for example):

telephone handset HT SVK <number of fibers> ZTT 2021 xxxxM

## 5. Optical Fiber


Standard	ITU-T G.652D ZTT-ALF®		
Optical	Fibre attenuation .. cabled	@ 1310 nm ≤0.38 dB/km	@ 1550 nm ≤0.23 dB/km
	Refractive index profile	Step	
	Mode field diameter (MFD)	9.2 ± 0.5 µm	-
	Zero dispersion wavelength	1300~1324 nm	
	Zero dispersion slope	≤0.092 ps/nm²·km	
	Dispersion coefficient	@ 1310 nm ≤3.5 ps/nm.km	@ 1550 nm ≤19.0 ps/nm.km
	PMD individual value	≤0.2 ps/√km	
	Cut-off wavelength	≤1260 nm	
	Macro bending loss .. 100 turns Ø60 mm	@1550 nm ≤0.05 dB	@1625 nm ≤0.10 dB
Geometric	Cladding diameter	125 ± 1.0 µm	
	Coating Diameter	250 ± 15 µm	
	Core/clad concentricity error	Max. individual value: 1µm Max. average value: ≤0.5µm	
Cladding non-circularity		≤1.0 %	
Mechanical	Proof stress	≥0.69 Gpa	

## 6. Test Methods

Test	Conditions	Acceptance criteria
Tensile strength IEC 60794-1-2 E1	Tensile strength: see Point 3 Length: ≥ 50 m, Duration: 1 min	- Fiber strain: ≤0.6%, Δα ≤0.15dB - Δα reversible after test
Crush resistance IEC 60794-1-2 E3	Crush: see Point 3 Test duration: 1 min, test number: 3	- Δα ≤0.05dB after test - No damage
Impact IEC 60794-1-2 E4	Impact energy: 3J R = 10 mm, number of places: 3	- Δα ≤0.05dB after test - No damage
Repeated bending IEC 60794-1-2 E6	Bending radius: 20x cable Ø 25 cycles	- Δα ≤0.05dB after test - No damage
Torsion IEC 60794-1-2 E7	Sample length: 2 m ± 180°, 10 cycles	- Δα ≤0.05dB after test - No damage
Bend IEC 60794-1-2 E11A	Bending radius: 10x cable Ø 3 turns, 3 cycles	- Δα ≤0.05dB after test - No damage
Temperature cycling IEC 60794-1-2 F1	-20°C → +60°C 4 hours at each step, 2 cycles	- Δα≤0.15dB/km and reversible
Water penetration IEC 60794-1-2 F5	Sample length: 3 m Water column height: 1 m Test duration: 24 h	- No leakage from outside of modules

All optical measurements at 1550 nm

## 7. Logistics

Cable type	Length Tolerance	4km -1% / +3%	 D*d*B in cm
GYFXT6P-6 G.652D	Drum Type Dimensions Weight	Wood 100*60*75 179 kg	

Dimensions including protection. Indicative values, actually delivered drum sizes and weights may deviate. Cable ends sealed with caps