
Spec No.: ZTT 22-XJ19646



# **TECHNICAL SPECIFICATION**





1. Optical Mini Module PLC Splitter, input port LC/APC pigtail length 1.5m,output port LC/APC pigtail length 1.5m,OD:0.9 ± 0.08mm, G657A1 fiber, colored hytrel.

#### 1.1 General properties:



## 1.2 Technical characteristics for splitter:

Туре	1X2	1X4	1X8	1X16	1X32	1X64	
Channel wavelength(nm)	1260-1650						
Insertion loss(dB)	≤4.0	≤7.3	≤10.5	≤13.8	≤17.0	≤20.3	
Loss Uniformity (dB)	≤0.6	≤0.6	≤0.8	≤1.2	≤1.5	≤1.8	
Return loss (dB)	≥55						
Polarization dependent loss(dB)	≤0.3	≤0.3	≤0,3	≤0,3	≤0.3	≤0.3	
Directivity(dB)	≥55						
Operating temperature (*C)	-40-+85						
Storage temperature(°C)	-40~+85						

Note 1: Above insertion loss values are measured at indoor temperature, not including the connector loss; Note 2: Insertion loss of PLC splitter with connectors, should plus 0.2dB base on above insertion loss.

#### 1.3 Application

 Installed in optical cross connecting cabinet and splitting box. The color can be adjusted according to customers' requirements.

#### 1.4 Feature

- Small size and aesthetic appearance.
- Color code:red, green, blue, yellow,white, grey, brown, violet.
- Standard compliance: Telecordia GR-1209 and GR-1221.
- Installation quick, reliable performance, stability.
- Employ integrated optic production process.
- Wide operating wavelength range.
- Good uniformity, in particular the application of PON.
- Dimnesion:4\*4\*40mm for 1\*2 Splitter, 4\*7\*50mm for 1\*4 Splitter .
- Comply with RoHS2.0.



# 1.5 Optical fiber

### G.657A1 Fiber

Category	Descrip	Specifications			
	Descrip	Before cable	After cable		
Zero Dispersion  Cable Cutoff v  Macro Bendin (10 turns; Ф30 (1 turns; Ф20 (1 turns; Ф20 (1 turns; Ф20	Attenuation	@1310 nm	≤0.35 dB/km	≤0.40 dB/km	
	Attenuation	@1550 nm	≤0.21 dB/km	≤0.30 dB/km	
	Zero Dispersion Wavelength	1300~1324 nm			
	Zero Dispersion Slope	≤ 0.092 ps/nm²·km			
	Cable Cutoff Wavelength (λ	≤1260 nm			
	Macro Bending Loss	tit.			
	(10 turns; Ф30 mm) @1550 nm		≤ 0.25 dB		
	(10 turns; Ф30 mm)	@1625 nm	≤ 1,0 dB		
	(1 turns; Ф20 mm)	@1550 nm	≤ 0.75 dB		
	(1 turns; Ф20 mm)	@1625 nm	≤ 1.5 dB		
	Mode Field Diameter	@1310 nm	(8.6-9.5)±0.4μm		
Dimensional Cl	Cladding Diameter	125±1μm			
	Cladding Non Circularity	≤1.0%			
	Core/Clad Concentricity Err	≤0.5µm			
Mechanical Specifications	Proof Stress	≥1.05%			